



Performance Pigments & Colors  
 FERRO (France) SARL  
 43, RUE JEANNE D'ARC  
 52115 SAINT-DIZIER CEDEX  
 France

**TEMPERATURE-TABLE for PTCR**  
 Higher quality products and lower costs through improved, reliable firing control

Type PTCR - ETH	Ring Colour : Green
Ferro no. : 1409477	Dimensions : ± 20 x 10 x 7,0 mm
Temperature Range °C : 850 - 1100°C	

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
		18,22	1058 °	18,72	1006 °	19,22	954 °	19,72	872 °		
		18,23	1057 °	18,73	1005 °	19,23	952 °	19,73	870 °		
		18,24	1056 °	18,74	1004 °	19,24	951 °	19,74	867 °		
		18,25	1055 °	18,75	1003 °	19,25	950 °	19,75	865 °		
		18,26	1054 °	18,76	1002 °	19,26	949 °	19,76	863 °		
		18,27	1053 °	18,77	1001 °	19,27	947 °	19,77	860 °		
		18,28	1052 °	18,78	1000 °	19,28	946 °	19,78	858 °		
		18,29	1051 °	18,79	999 °	19,29	945 °	19,79	855 °		
		18,30	1049 °	18,80	998 °	19,30	944 °	19,80	853 °		
		18,31	1048 °	18,81	997 °	19,31	942 °	19,81	850 °		
		18,32	1047 °	18,82	996 °	19,32	941 °				
17,83	1100 °	18,33	1046 °	18,83	995 °	19,33	940 °				
17,84	1099 °	18,34	1045 °	18,84	994 °	19,34	938 °				
17,85	1098 °	18,35	1044 °	18,85	993 °	19,35	937 °				
17,86	1097 °	18,36	1043 °	18,86	992 °	19,36	936 °				
17,87	1096 °	18,37	1042 °	18,87	991 °	19,37	934 °				
17,88	1095 °	18,38	1041 °	18,88	990 °	19,38	933 °				
17,89	1094 °	18,39	1040 °	18,89	989 °	19,39	931 °				
17,90	1093 °	18,40	1039 °	18,90	988 °	19,40	930 °				
17,91	1092 °	18,41	1038 °	18,91	987 °	19,41	928 °				
17,92	1090 °	18,42	1037 °	18,92	986 °	19,42	927 °				
17,93	1089 °	18,43	1036 °	18,93	985 °	19,43	925 °				
17,94	1088 °	18,44	1035 °	18,94	984 °	19,44	924 °				
17,95	1087 °	18,45	1034 °	18,95	983 °	19,45	922 °				
17,96	1086 °	18,46	1033 °	18,96	982 °	19,46	921 °				
17,97	1085 °	18,47	1031 °	18,97	981 °	19,47	919 °				
17,98	1084 °	18,48	1030 °	18,98	980 °	19,48	918 °				
17,99	1083 °	18,49	1029 °	18,99	979 °	19,49	916 °				
18,00	1082 °	18,50	1028 °	19,00	978 °	19,50	914 °				
18,01	1081 °	18,51	1027 °	19,01	977 °	19,51	913 °				
18,02	1080 °	18,52	1026 °	19,02	976 °	19,52	911 °				
18,03	1079 °	18,53	1025 °	19,03	975 °	19,53	909 °				
18,04	1078 °	18,54	1024 °	19,04	974 °	19,54	908 °				
18,05	1077 °	18,55	1023 °	19,05	973 °	19,55	906 °				
18,06	1076 °	18,56	1022 °	19,06	972 °	19,56	904 °				
18,07	1074 °	18,57	1021 °	19,07	971 °	19,57	902 °				
18,08	1073 °	18,58	1020 °	19,08	969 °	19,58	900 °				
18,09	1072 °	18,59	1019 °	19,09	968 °	19,59	899 °				
18,10	1071 °	18,60	1018 °	19,10	967 °	19,60	897 °				
18,11	1070 °	18,61	1017 °	19,11	966 °	19,61	895 °				
18,12	1069 °	18,62	1016 °	19,12	965 °	19,62	893 °				
18,13	1068 °	18,63	1015 °	19,13	964 °	19,63	891 °				
18,14	1067 °	18,64	1014 °	19,14	963 °	19,64	889 °				
18,15	1066 °	18,65	1013 °	19,15	962 °	19,65	887 °				
18,16	1065 °	18,66	1012 °	19,16	961 °	19,66	885 °				
18,17	1064 °	18,67	1011 °	19,17	959 °	19,67	883 °				
18,18	1062 °	18,68	1010 °	19,18	958 °	19,68	881 °				
18,19	1061 °	18,69	1009 °	19,19	957 °	19,69	879 °				
18,20	1060 °	18,70	1008 °	19,20	956 °	19,70	876 °				
18,21	1059 °	18,71	1007 °	19,21	955 °	19,71	874 °				

Powder Batch # : 79	Batch approved
Date : 14/12/2017	Quality Inspection :

For inquiries :  
 Customer Service Desk  
 Phone : +49 69 27116 432  
 Fax : +49 69 27116 243

