



FERRO ELECTRONIC MATERIAL SYSTEMS
 FERRO (HOLLAND) B.V.
 FRONTSTRAAT 2
 5405 PB UDEN
 THE NETHERLANDS

TEMPERATURE-TABLE for PTCR
 Higher quality products and lower costs through improved, reliable firing control

Type PTCR - LTH	:	4322 020 07061	Ring Colour	:	Red
Ferro No.	:	1007154	Dimensions	:	± 20 x 10 x 7,0 mm
Temperature Range °C	:	970 - 1250°C			

Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,36	1198 °	19,86	1076 °				
				19,37	1196 °	19,87	1072 °				
				19,38	1195 °	19,88	1067 °				
				19,39	1193 °	19,89	1063 °				
				19,40	1192 °	19,90	1059 °				
				19,41	1190 °	19,91	1054 °				
				19,42	1188 °	19,92	1050 °				
				19,43	1187 °	19,93	1045 °				
				19,44	1185 °	19,94	1040 °				
				19,45	1184 °	19,95	1035 °				
				19,46	1182 °	19,96	1030 °				
				19,47	1180 °	19,97	1025 °				
				19,48	1179 °	19,98	1020 °				
				19,49	1177 °	19,99	1015 °				
				19,50	1175 °	20,00	1009 °				
		19,01	1251 °	19,51	1173 °	20,01	1004 °				
		19,02	1249 °	19,52	1171 °	20,02	998 °				
		19,03	1247 °	19,53	1169 °	20,03	992 °				
		19,04	1245 °	19,54	1168 °	20,04	986 °				
		19,05	1244 °	19,55	1166 °	20,05	980 °				
		19,06	1242 °	19,56	1164 °	20,06	974 °				
		19,07	1240 °	19,57	1161 °	20,07	968 °				
		19,08	1239 °	19,58	1159 °						
		19,09	1237 °	19,59	1157 °						
		19,10	1235 °	19,60	1155 °						
		19,11	1234 °	19,61	1153 °						
		19,12	1232 °	19,62	1150 °						
		19,13	1231 °	19,63	1148 °						
		19,14	1229 °	19,64	1146 °						
		19,15	1228 °	19,65	1143 °						
		19,16	1226 °	19,66	1141 °						
		19,17	1225 °	19,67	1138 °						
		19,18	1223 °	19,68	1135 °						
		19,19	1222 °	19,69	1133 °						
		19,20	1220 °	19,70	1130 °						
		19,21	1219 °	19,71	1127 °						
		19,22	1218 °	19,72	1124 °						
		19,23	1216 °	19,73	1121 °						
		19,24	1215 °	19,74	1118 °						
		19,25	1213 °	19,75	1115 °						
		19,26	1212 °	19,76	1112 °						
		19,27	1210 °	19,77	1109 °						
		19,28	1209 °	19,78	1105 °						
		19,29	1208 °	19,79	1102 °						
		19,30	1206 °	19,80	1098 °						
		19,31	1205 °	19,81	1095 °						
		19,32	1203 °	19,82	1091 °						
		19,33	1202 °	19,83	1088 °						
		19,34	1201 °	19,84	1084 °						
		19,35	1199 °	19,85	1080 °						

Powder Batch #	:	131	Batch approved	
Date:	:	4-5-2010	Quality inspection:	<i>BUH</i>

For inquiries:
 Customer Service Desk
 Phone : +31 (0) 413 283245
 Fax : +31 (0) 413 265219

