



Performance Pigments & Colors

FERRO (FRANCE) SARL
43, RUE JEANNE D'ARC
52115 SAINT-DIZIER CEDEX
FRANCE

TEMPERATURE-TABLE for PTCR

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - LTH : 4322 020 07061						Ring Colour : Red					
Ferro No. : 1007154			Dimensions : ± 20 x 10 x 7,0 mm								
Temperature Range °C : 970 - 1250°C											
Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,18	1205 °	19,68	1121 °				
				19,19	1204 °	19,69	1118 °				
				19,20	1203 °	19,70	1115 °				
				19,21	1202 °	19,71	1112 °				
				19,22	1201 °	19,72	1109 °				
				19,23	1199 °	19,73	1106 °				
				19,24	1198 °	19,74	1103 °				
				19,25	1197 °	19,75	1100 °				
				19,26	1196 °	19,76	1096 °				
				19,27	1195 °	19,77	1093 °				
				19,28	1194 °	19,78	1090 °				
				19,29	1192 °	19,79	1086 °				
				19,30	1191 °	19,80	1083 °				
	18,81	1250 °		19,31	1190 °	19,81	1079 °				
	18,82	1249 °		19,32	1189 °	19,82	1075 °				
				18,83	1247 °	19,33	1187 °	19,83	1072 °		
				18,84	1246 °	19,34	1186 °	19,84	1068 °		
				18,85	1244 °	19,35	1185 °	19,85	1064 °		
				18,86	1243 °	19,36	1183 °	19,86	1060 °		
				18,87	1241 °	19,37	1182 °	19,87	1056 °		
				18,88	1240 °	19,38	1180 °	19,88	1051 °		
				18,89	1239 °	19,39	1179 °	19,89	1047 °		
				18,90	1237 °	19,40	1178 °	19,90	1043 °		
				18,91	1236 °	19,41	1176 °	19,91	1038 °		
				18,92	1235 °	19,42	1175 °	19,92	1034 °		
				18,93	1233 °	19,43	1173 °	19,93	1029 °		
				18,94	1232 °	19,44	1171 °	19,94	1024 °		
				18,95	1231 °	19,45	1170 °	19,95	1019 °		
				18,96	1230 °	19,46	1168 °	19,96	1014 °		
				18,97	1228 °	19,47	1166 °	19,97	1009 °		
				18,98	1227 °	19,48	1165 °	19,98	1004 °		
				18,99	1226 °	19,49	1163 °	19,99	999 °		
				19,00	1225 °	19,50	1161 °	20,00	994 °		
				19,01	1224 °	19,51	1159 °	20,01	988 °		
				19,02	1223 °	19,52	1157 °	20,02	983 °		
				19,03	1221 °	19,53	1155 °	20,03	977 °		
				19,04	1220 °	19,54	1153 °	20,04	971 °		
				19,05	1219 °	19,55	1151 °	20,05	965 °		
				19,06	1218 °	19,56	1149 °				
				19,07	1217 °	19,57	1147 °				
				19,08	1216 °	19,58	1145 °				
				19,09	1215 °	19,59	1143 °				
				19,10	1214 °	19,60	1141 °				
				19,11	1213 °	19,61	1138 °				
				19,12	1212 °	19,62	1136 °				
				19,13	1211 °	19,63	1134 °				
				19,14	1209 °	19,64	1131 °				
				19,15	1208 °	19,65	1128 °				
				19,16	1207 °	19,66	1126 °				
				19,17	1206 °	19,67	1123 °				

Powder Batch # : 137
Date: 04/07/2012Batch approved
Quality Inspection:

For inquiries:

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243

sheet 367- 137 - 010

