




Performance Pigments & Colors

FERRO (FRANCE) SARL
43, RUE JEANNE D'ARC
52115 SAINT-DIZIER CEDEX
FRANCE

TEMPERATURE-TABLE for PTCR											
Higher quality products and lower costs through improved, reliable firing control											
Type PTCR - LTH	4322 020 07061				Ring Colour	Red					
Ferro No.	1007154				Dimensions	± 20 x 10 x 7,0 mm					
Temperature Range °C	970 - 1250°C										
Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,18	1201 °	19,68	1118 °				
				19,19	1200 °	19,69	1115 °				
				19,20	1199 °	19,70	1112 °				
				19,21	1198 °	19,71	1110 °				
				19,22	1196 °	19,72	1107 °				
				19,23	1195 °	19,73	1104 °				
				19,24	1194 °	19,74	1101 °				
				19,25	1193 °	19,75	1098 °				
				19,26	1192 °	19,76	1095 °				
				19,27	1190 °	19,77	1092 °				
				19,28	1189 °	19,78	1089 °				
				19,29	1188 °	19,79	1085 °				
				19,30	1186 °	19,80	1082 °				
				19,31	1185 °	19,81	1079 °				
	18,82	1251 °		19,32	1184 °	19,82	1075 °				
	18,83	1249 °		19,33	1183 °	19,83	1072 °				
	18,84	1247 °		19,34	1181 °	19,84	1068 °				
	18,85	1246 °		19,35	1180 °	19,85	1064 °				
	18,86	1244 °		19,36	1178 °	19,86	1061 °				
	18,87	1242 °		19,37	1177 °	19,87	1057 °				
	18,88	1241 °		19,38	1176 °	19,88	1053 °				
	18,89	1239 °		19,39	1174 °	19,89	1049 °				
	18,90	1238 °		19,40	1173 °	19,90	1045 °				
	18,91	1236 °		19,41	1171 °	19,91	1041 °				
	18,92	1235 °		19,42	1170 °	19,92	1037 °				
	18,93	1233 °		19,43	1168 °	19,93	1032 °				
	18,94	1232 °		19,44	1167 °	19,94	1028 °				
	18,95	1230 °		19,45	1165 °	19,95	1023 °				
	18,96	1229 °		19,46	1163 °	19,96	1019 °				
	18,97	1227 °		19,47	1162 °	19,97	1014 °				
	18,98	1226 °		19,48	1160 °	19,98	1009 °				
	18,99	1225 °		19,49	1158 °	19,99	1005 °				
	19,00	1223 °		19,50	1157 °	20,00	1000 °				
	19,01	1222 °		19,51	1155 °	20,01	995 °				
	19,02	1221 °		19,52	1153 °	20,02	989 °				
	19,03	1220 °		19,53	1151 °	20,03	984 °				
	19,04	1218 °		19,54	1149 °	20,04	979 °				
	19,05	1217 °		19,55	1147 °	20,05	973 °				
	19,06	1216 °		19,56	1145 °	20,06	968 °				
	19,07	1214 °		19,57	1143 °						
	19,08	1213 °		19,58	1141 °						
	19,09	1212 °		19,59	1139 °						
	19,10	1211 °		19,60	1137 °						
	19,11	1210 °		19,61	1135 °						
	19,12	1208 °		19,62	1132 °						
	19,13	1207 °		19,63	1130 °						
	19,14	1206 °		19,64	1128 °						
	19,15	1205 °		19,65	1125 °						
	19,16	1204 °		19,66	1123 °						
	19,17	1202 °		19,67	1120 °						

Powder Batch # : 140 Batch approved 
Date : 21/05/2013 Quality Inspection :

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243

