


TEMPERATURE-TABLE for PTCR
Higher quality products and lower costs through improved, reliable firing control

Type PTCR - LTH	Ring Colour : Red
Ferro No. : 1400604	Dimensions : ± 20 x 10 x 7,0 mm
Temperature Range °C : 970 - 1250°C	

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,28	1202 °	19,78	1094 °				
				19,29	1200 °	19,79	1091 °				
				19,30	1199 °	19,80	1087 °				
				19,31	1198 °	19,81	1083 °				
				19,32	1196 °	19,82	1079 °				
				19,33	1195 °	19,83	1075 °				
				19,34	1193 °	19,84	1071 °				
				19,35	1192 °	19,85	1067 °				
				19,36	1191 °	19,86	1062 °				
				19,37	1189 °	19,87	1058 °				
				19,38	1188 °	19,88	1054 °				
				19,39	1186 °	19,89	1049 °				
				19,40	1185 °	19,90	1044 °				
				19,41	1183 °	19,91	1039 °				
				19,42	1181 °	19,92	1034 °				
				19,43	1180 °	19,93	1029 °				
				19,44	1178 °	19,94	1024 °				
				19,45	1177 °	19,95	1019 °				
				19,46	1175 °	19,96	1014 °				
		18,97	1250 °	19,47	1173 °	19,97	1008 °				
		18,98	1248 °	19,48	1171 °	19,98	1002 °				
		18,99	1246 °	19,49	1170 °	19,99	997 °				
		19,00	1245 °	19,50	1168 °	20,00	991 °				
		19,01	1243 °	19,51	1166 °	20,01	985 °				
		19,02	1241 °	19,52	1164 °	20,02	979 °				
		19,03	1239 °	19,53	1162 °	20,03	972 °				
		19,04	1237 °	19,54	1160 °	20,04	966 °				
		19,05	1236 °	19,55	1158 °						
		19,06	1234 °	19,56	1156 °						
		19,07	1232 °	19,57	1154 °						
		19,08	1231 °	19,58	1152 °						
		19,09	1229 °	19,59	1149 °						
		19,10	1227 °	19,60	1147 °						
		19,11	1226 °	19,61	1145 °						
		19,12	1224 °	19,62	1142 °						
		19,13	1223 °	19,63	1140 °						
		19,14	1221 °	19,64	1137 °						
		19,15	1220 °	19,65	1135 °						
		19,16	1219 °	19,66	1132 °						
		19,17	1217 °	19,67	1129 °						
		19,18	1216 °	19,68	1126 °						
		19,19	1214 °	19,69	1124 °						
		19,20	1213 °	19,70	1121 °						
		19,21	1211 °	19,71	1118 °						
		19,22	1210 °	19,72	1115 °						
		19,23	1209 °	19,73	1111 °						
		19,24	1207 °	19,74	1108 °						
		19,25	1206 °	19,75	1105 °						
		19,26	1205 °	19,76	1101 °						
		19,27	1203 °	19,77	1098 °						

Powder Batch # : 150	Batch approved
Date : 05/01/2017	Quality Inspection : 

For inquiries :
Customer Service Desk
Phone : +49 69 27116 432
Fax : +49 69 27116 243

