

TEMPERATURE-TABLE for PTCR											
Higher quality products and lower costs through improved, reliable firing control											
Type PTCR - LTH						Ring Colour : Red					
Ferro No. : 1400604						Dimensions : ± 20 x 10 x 7,0 mm					
Temperature Range °C	: 970 - 1250°C					Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
Ring diameter mm	Ring temperature °C	Ring diameter mm	Ring temperature °C	Ring diameter mm	Ring temperature °C	Ring diameter mm	Ring temperature °C	Ring diameter mm	Ring temperature °C	Ring diameter mm	Ring temperature °C
				19,36	1194 °	19,86	1090 °				
				19,37	1193 °	19,87	1086 °				
				19,38	1191 °	19,88	1083 °				
				19,39	1190 °	19,89	1079 °				
				19,40	1189 °	19,90	1076 °				
				19,41	1187 °	19,91	1072 °				
				19,42	1186 °	19,92	1068 °				
				19,43	1184 °	19,93	1064 °				
				19,44	1183 °	19,94	1060 °				
				19,45	1182 °	19,95	1056 °				
				19,46	1180 °	19,96	1052 °				
			18,98	1251 °	19,47	1179 °	19,97	1048 °			
			18,99	1249 °	19,48	1177 °	19,98	1043 °			
			19,00	1247 °	19,49	1176 °	19,99	1039 °			
			19,01	1245 °	19,50	1174 °	20,00	1034 °			
			19,02	1243 °	19,51	1172 °	20,01	1030 °			
			19,03	1241 °	19,52	1171 °	20,02	1025 °			
			19,04	1240 °	19,53	1169 °	20,03	1020 °			
			19,05	1238 °	19,54	1168 °	20,04	1015 °			
			19,06	1236 °	19,55	1166 °	20,05	1010 °			
			19,07	1235 °	19,56	1164 °	20,06	1005 °			
			19,08	1233 °	19,57	1162 °	20,07	1000 °			
			19,09	1231 °	19,58	1161 °	20,08	994 °			
			19,10	1230 °	19,59	1159 °	20,09	989 °			
			19,11	1228 °	19,60	1157 °	20,10	983 °			
			19,12	1227 °	19,61	1155 °	20,11	978 °			
			19,13	1225 °	19,62	1153 °	20,12	972 °			
			19,14	1224 °	19,63	1151 °	20,13	966 °			
			19,15	1222 °	19,64	1149 °					
			19,16	1221 °	19,65	1147 °					
			19,17	1219 °	19,66	1145 °					
			19,18	1218 °	19,67	1142 °					
			19,19	1217 °	19,68	1140 °					
			19,20	1215 °	19,69	1138 °					
			19,21	1214 °	19,70	1136 °					
			19,22	1212 °	19,71	1133 °					
			19,23	1211 °	19,72	1131 °					
			19,24	1210 °	19,73	1128 °					
			19,25	1208 °	19,74	1126 °					
			19,26	1207 °	19,75	1123 °					
			19,27	1206 °	19,76	1120 °					
			19,28	1205 °	19,77	1118 °					
			19,29	1203 °	19,78	1115 °					
			19,30	1202 °	19,79	1112 °					
			19,31	1201 °	19,80	1109 °					
			19,32	1199 °	19,81	1106 °					
			19,33	1198 °	19,82	1103 °					
			19,34	1197 °	19,83	1100 °					
			19,35	1195 °	19,84	1097 °					
					19,85	1093 °					

Powder Batch # : 152  
 Date : 26/04/2017

Batch approved  
 Quality Inspection :

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243