



Performance Pigments & Colors

FERRO (FRANCE) SARL
43, RUE JEANNE D'ARC
52115 SAINT-DIZIER CEDEX
FRANCE

TEMPERATURE-TABLE for PTCR

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - LTH						Ring Colour		Red					
Ferro No.		1400604				Dimensions		± 20 x 10 x 7,0 mm					
Temperature Range °C		970 - 1250°C											
Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,18	1202 °	19,68	1123 °						
				19,19	1201 °	19,69	1120 °						
				19,20	1200 °	19,70	1118 °						
				19,21	1199 °	19,71	1115 °						
				19,22	1197 °	19,72	1113 °						
				19,23	1196 °	19,73	1110 °						
				19,24	1195 °	19,74	1107 °						
				19,25	1194 °	19,75	1105 °						
				19,26	1193 °	19,76	1102 °						
				19,27	1192 °	19,77	1099 °						
				19,28	1190 °	19,78	1096 °						
				19,29	1189 °	19,79	1093 °						
	18,80	1251 °		19,30	1188 °	19,80	1090 °						
	18,81	1249 °		19,31	1187 °	19,81	1087 °						
	18,82	1247 °		19,32	1185 °	19,82	1084 °						
	18,83	1246 °		19,33	1184 °	19,83	1081 °						
	18,84	1244 °		19,34	1183 °	19,84	1077 °						
	18,85	1243 °		19,35	1182 °	19,85	1074 °						
	18,86	1241 °		19,36	1180 °	19,86	1070 °						
	18,87	1240 °		19,37	1179 °	19,87	1067 °						
	18,88	1238 °		19,38	1177 °	19,88	1063 °						
	18,89	1237 °		19,39	1176 °	19,89	1060 °						
	18,90	1236 °		19,40	1175 °	19,90	1056 °						
	18,91	1234 °		19,41	1173 °	19,91	1052 °						
	18,92	1233 °		19,42	1172 °	19,92	1048 °						
	18,93	1232 °		19,43	1170 °	19,93	1044 °						
	18,94	1230 °		19,44	1169 °	19,94	1040 °						
	18,95	1229 °		19,45	1167 °	19,95	1036 °						
	18,96	1228 °		19,46	1166 °	19,96	1032 °						
	18,97	1226 °		19,47	1164 °	19,97	1028 °						
	18,98	1225 °		19,48	1163 °	19,98	1024 °						
	18,99	1224 °		19,49	1161 °	19,99	1019 °						
	19,00	1223 °		19,50	1159 °	20,00	1015 °						
	19,01	1222 °		19,51	1158 °	20,01	1010 °						
	19,02	1220 °		19,52	1156 °	20,02	1005 °						
	19,03	1219 °		19,53	1154 °	20,03	1001 °						
	19,04	1218 °		19,54	1152 °	20,04	996 °						
	19,05	1217 °		19,55	1150 °	20,05	991 °						
	19,06	1216 °		19,56	1149 °	20,06	986 °						
	19,07	1214 °		19,57	1147 °	20,07	981 °						
	19,08	1213 °		19,58	1145 °								
	19,09	1212 °		19,59	1143 °								
	19,10	1211 °		19,60	1141 °								
	19,11	1210 °		19,61	1139 °								
	19,12	1209 °		19,62	1137 °								
	19,13	1208 °		19,63	1134 °								
	19,14	1207 °		19,64	1132 °								
	19,15	1205 °		19,65	1130 °								
	19,16	1204 °		19,66	1128 °								
	19,17	1203 °		19,67	1125 °								

Powder Batch # : 166
Date : 17/11/2020Batch approved
Quality Inspection :

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243