


TEMPERATURE-TABLE for PTCR
Higher quality products and lower costs through improved, reliable firing control

Type PTCR - LTH						Ring Colour : Red					
Ferro No. : 1400604						Dimensions : ± 20 x 10 x 7,0 mm					
Temperature Range °C : 970 - 1250°C											

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,18	1207 °	19,68	1121 °				
				19,19	1206 °	19,69	1119 °				
				19,20	1205 °	19,70	1116 °				
				19,21	1203 °	19,71	1113 °				
				19,22	1202 °	19,72	1111 °				
				19,23	1201 °	19,73	1108 °				
				19,24	1199 °	19,74	1105 °				
				19,25	1198 °	19,75	1103 °				
				19,26	1197 °	19,76	1100 °				
				19,27	1195 °	19,77	1097 °				
				19,28	1194 °	19,78	1094 °				
				19,29	1193 °	19,79	1091 °				
				19,30	1191 °	19,80	1088 °				
				19,31	1190 °	19,81	1085 °				
				19,32	1188 °	19,82	1082 °				
				19,33	1187 °	19,83	1079 °				
		18,85	1250 °	19,34	1186 °	19,84	1075 °				
		18,86	1249 °	19,35	1184 °	19,85	1072 °				
		18,87	1247 °	19,36	1183 °	19,86	1069 °				
				19,37	1181 °	19,87	1065 °				
		18,88	1246 °	19,38	1180 °	19,88	1062 °				
		18,89	1244 °	19,39	1178 °	19,89	1058 °				
		18,90	1243 °	19,40	1177 °	19,90	1055 °				
		18,91	1242 °	19,41	1175 °	19,91	1051 °				
		18,92	1240 °	19,42	1173 °	19,92	1048 °				
		18,93	1239 °	19,43	1172 °	19,93	1044 °				
		18,94	1238 °	19,44	1170 °	19,94	1040 °				
		18,95	1236 °	19,45	1168 °	19,95	1036 °				
		18,96	1235 °	19,46	1167 °	19,96	1032 °				
		18,97	1234 °	19,47	1165 °	19,97	1028 °				
		18,98	1232 °	19,48	1163 °	19,98	1024 °				
		18,99	1231 °	19,49	1161 °	19,99	1020 °				
		19,00	1230 °	19,50	1160 °	20,00	1016 °				
		19,01	1229 °	19,51	1158 °	20,01	1011 °				
		19,02	1227 °	19,52	1156 °	20,02	1007 °				
		19,03	1226 °	19,53	1154 °	20,03	1003 °				
		19,04	1225 °	19,54	1152 °	20,04	998 °				
		19,05	1223 °	19,55	1150 °	20,05	994 °				
		19,06	1222 °	19,56	1148 °	20,06	989 °				
		19,07	1221 °	19,57	1146 °	20,07	984 °				
		19,08	1220 °	19,58	1144 °	20,08	980 °				
		19,09	1218 °	19,59	1142 °	20,09	975 °				
		19,10	1217 °	19,60	1140 °	20,10	970 °				
		19,11	1216 °	19,61	1137 °						
		19,12	1215 °	19,62	1135 °						
		19,13	1213 °	19,63	1133 °						
		19,14	1212 °	19,64	1131 °						
		19,15	1211 °	19,65	1128 °						
		19,16	1210 °	19,66	1126 °						
		19,17	1208 °	19,67	1124 °						

Powder Batch # : 167	Batch approved
Date : 07/04/2021	Quality Inspection 

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243

