


TEMPERATURE-TABLE for PTCR

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - LTH		Ring Colour	: Red
Ferro No.	: 1400604	Dimensions	: ± 20 x 10 x 7,0 mm
Temperature Range °C	: 970 - 1250°C		

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				19,18	1212 °	19,68	1127 °				
				19,19	1210 °	19,69	1124 °				
				19,20	1209 °	19,70	1122 °				
				19,21	1207 °	19,71	1119 °				
				19,22	1206 °	19,72	1116 °				
				19,23	1205 °	19,73	1113 °				
				19,24	1203 °	19,74	1111 °				
				19,25	1202 °	19,75	1108 °				
				19,26	1200 °	19,76	1105 °				
				19,27	1199 °	19,77	1102 °				
				19,28	1198 °	19,78	1099 °				
				19,29	1196 °	19,79	1096 °				
				19,30	1195 °	19,80	1092 °				
				19,31	1193 °	19,81	1089 °				
				19,32	1192 °	19,82	1086 °				
				19,33	1190 °	19,83	1082 °				
				19,34	1189 °	19,84	1079 °				
				19,35	1188 °	19,85	1075 °				
				19,36	1186 °	19,86	1071 °				
				19,37	1185 °	19,87	1068 °				
				19,38	1183 °	19,88	1064 °				
				19,39	1182 °	19,89	1060 °				
				19,40	1180 °	19,90	1056 °				
				19,41	1179 °	19,91	1052 °				
				19,42	1177 °	19,92	1047 °				
				19,43	1176 °	19,93	1043 °				
		18,95	1251 °	19,44	1174 °	19,94	1039 °				
		18,96	1249 °	19,45	1172 °	19,95	1034 °				
		18,97	1247 °	19,46	1171 °	19,96	1030 °				
				19,47	1169 °	19,97	1025 °				
		18,98	1245 °	19,48	1168 °	19,98	1020 °				
		18,99	1243 °	19,49	1166 °	19,99	1015 °				
		19,00	1241 °	19,50	1164 °	20,00	1011 °				
		19,01	1240 °	19,51	1162 °	20,01	1005 °				
		19,02	1238 °	19,52	1161 °	20,02	1000 °				
		19,03	1236 °	19,53	1159 °	20,03	995 °				
		19,04	1234 °	19,54	1157 °	20,04	990 °				
		19,05	1232 °	19,55	1155 °	20,05	984 °				
		19,06	1231 °	19,56	1153 °	20,06	979 °				
		19,07	1229 °	19,57	1151 °	20,07	973 °				
		19,08	1227 °	19,58	1149 °	20,08	967 °				
		19,09	1226 °	19,59	1147 °						
		19,10	1224 °	19,60	1145 °						
		19,11	1222 °	19,61	1143 °						
		19,12	1221 °	19,62	1141 °						
		19,13	1219 °	19,63	1139 °						
		19,14	1218 °	19,64	1136 °						
		19,15	1216 °	19,65	1134 °						
		19,16	1215 °	19,66	1132 °						
		19,17	1213 °	19,67	1129 °						

Powder Batch #	: 170	Batch approved	
Date	: 24/11/2021	Quality Inspection	

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243

