

TEMPERATURE-TABLE for PTCR
 Higher quality products and lower costs through improved, reliable firing control

Type PTCR - STH	:	4322 020 07071	Ring Colour	:	Green
Ferro no.	:	1007156	Dimensions	:	± 20 x 10 x 7,0 mm
Temperature Range °C	:	1130 - 1400°C			

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
18,08	1400 °	18,57	1358 °	19,07	1290 °	19,57	1198 °				
18,09	1400 °	18,58	1357 °	19,08	1289 °	19,58	1196 °				
18,10	1399 °	18,59	1356 °	19,09	1287 °	19,59	1194 °				
18,11	1398 °	18,60	1355 °	19,10	1285 °	19,60	1191 °				
18,12	1398 °	18,61	1354 °	19,11	1284 °	19,61	1189 °				
18,13	1397 °	18,62	1353 °	19,12	1282 °	19,62	1187 °				
18,14	1397 °	18,63	1352 °	19,13	1280 °	19,63	1185 °				
18,15	1396 °	18,64	1350 °	19,14	1279 °	19,64	1183 °				
18,16	1395 °	18,65	1349 °	19,15	1277 °	19,65	1181 °				
18,17	1395 °	18,66	1348 °	19,16	1275 °	19,66	1179 °				
18,18	1394 °	18,67	1347 °	19,17	1274 °	19,67	1176 °				
18,19	1394 °	18,68	1346 °	19,18	1272 °	19,68	1174 °				
18,20	1393 °	18,69	1344 °	19,19	1270 °	19,69	1172 °				
18,21	1392 °	18,70	1343 °	19,20	1268 °	19,70	1170 °				
18,22	1392 °	18,71	1342 °	19,21	1267 °	19,71	1168 °				
18,22	1391 °	18,72	1341 °	19,22	1265 °	19,72	1165 °				
18,23	1390 °	18,73	1339 °	19,23	1263 °	19,73	1163 °				
18,24	1389 °	18,74	1338 °	19,24	1261 °	19,74	1161 °				
18,25	1389 °	18,75	1337 °	19,25	1260 °	19,75	1159 °				
18,26	1388 °	18,76	1335 °	19,26	1258 °	19,76	1156 °				
18,27	1387 °	18,77	1334 °	19,27	1256 °	19,77	1154 °				
18,28	1386 °	18,78	1333 °	19,28	1254 °	19,78	1152 °				
18,29	1385 °	18,79	1331 °	19,29	1252 °	19,79	1150 °				
18,30	1385 °	18,80	1330 °	19,30	1251 °	19,80	1147 °				
18,31	1384 °	18,81	1329 °	19,31	1249 °	19,81	1145 °				
18,32	1383 °	18,82	1327 °	19,32	1247 °	19,82	1143 °				
18,33	1382 °	18,83	1326 °	19,33	1245 °	19,83	1140 °				
18,34	1381 °	18,84	1325 °	19,34	1243 °	19,84	1138 °				
18,35	1380 °	18,85	1323 °	19,35	1241 °	19,85	1136 °				
18,36	1379 °	18,86	1322 °	19,36	1239 °	19,86	1133 °				
18,37	1379 °	18,87	1320 °	19,37	1238 °	19,87	1131 °				
18,38	1378 °	18,88	1319 °	19,38	1236 °	19,88	1129 °				
18,39	1377 °	18,89	1318 °	19,39	1234 °						
18,40	1376 °	18,90	1316 °	19,40	1232 °						
18,41	1375 °	18,91	1315 °	19,41	1230 °						
18,42	1374 °	18,92	1313 °	19,42	1228 °						
18,43	1373 °	18,93	1312 °	19,43	1226 °						
18,44	1372 °	18,94	1310 °	19,44	1224 °						
18,45	1371 °	18,95	1309 °	19,45	1222 °						
18,46	1370 °	18,96	1307 °	19,46	1220 °						
18,47	1369 °	18,97	1306 °	19,47	1218 °						
18,48	1368 °	18,98	1304 °	19,48	1216 °						
18,49	1367 °	18,99	1303 °	19,49	1214 °						
18,50	1366 °	19,00	1301 °	19,50	1212 °						
18,51	1365 °	19,01	1300 °	19,51	1210 °						
18,52	1364 °	19,02	1298 °	19,52	1208 °						
18,53	1363 °	19,03	1297 °	19,53	1206 °						
18,54	1362 °	19,04	1295 °	19,54	1204 °						
18,55	1361 °	19,05	1293 °	19,55	1202 °						
18,56	1360 °	19,06	1292 °	19,56	1200 °						

Powder Batch #	:	241	Batch approved	
Date:	:	3-12-2009	Quality Inspection:	<i>SH UM</i>

For inquiries:

Customer Service Desk

Phone : +31 (0) 413 283245

Fax : +31 (0) 413 265219

