


**TEMPERATURE-TABLE for PTCR**

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - STH : 4322 020 07071	Ring Colour : Green
Ferro no. : 1007156	Dimensions : ± 20 x 10 x 7,0 mm
Temperature Range °C : 1130 - 1400°C	

Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
		18,41	1342°	18,91	1282°	19,41	1210°				
		18,42	1341°	18,92	1281°	19,42	1209°				
		18,43	1340°	18,93	1280°	19,43	1207°				
		18,44	1339°	18,94	1279°	19,44	1205°				
		18,45	1337°	18,95	1277°	19,45	1204°				
17,96	1400°	18,46	1336°	18,96	1276°	19,46	1202°				
17,97	1399°	18,47	1335°	18,97	1275°	19,47	1200°				
17,98	1397°	18,48	1334°	18,98	1273°	19,48	1199°				
17,99	1396°	18,49	1333°	18,99	1272°	19,49	1197°				
18,00	1394°	18,50	1332°	19,00	1271°	19,50	1195°				
18,01	1393°	18,51	1330°	19,01	1269°	19,51	1194°				
18,02	1392°	18,52	1329°	19,02	1268°	19,52	1192°				
18,03	1390°	18,53	1328°	19,03	1267°	19,53	1190°				
18,04	1389°	18,54	1327°	19,04	1265°	19,54	1188°				
18,05	1387°	18,55	1326°	19,05	1264°	19,55	1187°				
18,06	1386°	18,56	1325°	19,06	1263°	19,56	1185°				
18,07	1384°	18,57	1323°	19,07	1261°	19,57	1183°				
18,08	1383°	18,58	1322°	19,08	1260°	19,58	1181°				
18,09	1382°	18,59	1321°	19,09	1258°	19,59	1180°				
18,10	1380°	18,60	1320°	19,10	1257°	19,60	1178°				
18,11	1379°	18,61	1319°	19,11	1256°	19,61	1176°				
18,12	1378°	18,62	1318°	19,12	1254°	19,62	1174°				
18,13	1376°	18,63	1316°	19,13	1253°	19,63	1173°				
18,14	1375°	18,64	1315°	19,14	1251°	19,64	1171°				
18,15	1374°	18,65	1314°	19,15	1250°	19,65	1169°				
18,16	1373°	18,66	1313°	19,16	1248°	19,66	1167°				
18,17	1371°	18,67	1312°	19,17	1247°	19,67	1166°				
18,18	1370°	18,68	1311°	19,18	1246°	19,68	1164°				
18,19	1369°	18,69	1309°	19,19	1244°	19,69	1162°				
18,20	1367°	18,70	1308°	19,20	1243°	19,70	1160°				
18,21	1366°	18,71	1307°	19,21	1241°	19,71	1158°				
18,22	1365°	18,72	1306°	19,22	1240°	19,72	1156°				
18,23	1364°	18,73	1305°	19,23	1238°	19,73	1155°				
18,24	1362°	18,74	1303°	19,24	1237°	19,74	1153°				
18,25	1361°	18,75	1302°	19,25	1235°	19,75	1151°				
18,26	1360°	18,76	1301°	19,26	1234°	19,85	1132°				
18,27	1359°	18,77	1300°	19,27	1232°	19,86	1130°				
18,28	1357°	18,78	1299°	19,28	1231°						
18,29	1356°	18,79	1297°	19,29	1229°						
18,30	1355°	18,80	1295°	19,30	1228°						
18,31	1354°	18,81	1294°	19,31	1226°						
18,32	1353°	18,82	1294°	19,32	1224°						
18,33	1351°	18,83	1292°	19,33	1223°						
18,34	1350°	18,84	1291°	19,34	1221°						
18,35	1349°	18,85	1290°	19,35	1220°						
18,36	1348°	18,86	1289°	19,36	1218°						
18,37	1347°	18,87	1287°	19,37	1217°						
18,38	1346°	18,88	1286°	19,38	1215°						
18,39	1344°	18,89	1285°	19,39	1213°						
18,40	1343°	18,90	1284°	19,40	1212°						

Powder Batch # : 253	Batch approved
Date: 20/10/2011	Quality Inspection: 

For inquiries:  
 Customer Service Desk  
 Phone : +49 69 27116 432  
 Fax : +49 69 27116 243