


TEMPERATURE-TABLE for PTCR

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - STH		Ring Colour : Green
Ferro no. : 1400606		Dimensions : ± 20 x 10 x 7,0 mm
Temperature Range °C : 1130 - 1400°C		

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				18,24	1328 °	18,74	1264 °	19,24	1207 °	19,74	1143 °
				18,25	1326 °	18,75	1263 °	19,25	1206 °	19,75	1142 °
				18,26	1325 °	18,76	1262 °	19,26	1205 °	19,76	1140 °
				18,27	1323 °	18,77	1261 °	19,27	1203 °	19,77	1139 °
				18,28	1322 °	18,78	1260 °	19,28	1202 °	19,78	1136 °
				18,29	1321 °	18,79	1259 °	19,29	1201 °	19,79	1136 °
				18,30	1319 °	18,80	1258 °	19,30	1200 °	19,80	1135 °
				18,31	1318 °	18,81	1256 °	19,31	1199 °	19,81	1133 °
		17,82	1401 °	18,32	1316 °	18,82	1255 °	19,32	1197 °	19,82	1132 °
		17,83	1398 °	18,33	1315 °	18,83	1254 °	19,33	1196 °	19,83	1131 °
		17,84	1396 °	18,34	1314 °	18,84	1253 °	19,34	1195 °	19,84	1129 °
		17,85	1394 °	18,35	1312 °	18,85	1252 °	19,35	1194 °		
		17,86	1392 °	18,36	1311 °	18,86	1251 °	19,36	1193 °		
		17,87	1390 °	18,37	1310 °	18,87	1250 °	19,37	1191 °		
		17,88	1388 °	18,38	1308 °	18,88	1248 °	19,38	1190 °		
		17,89	1386 °	18,39	1307 °	18,89	1247 °	19,39	1189 °		
		17,90	1385 °	18,40	1306 °	18,90	1246 °	19,40	1188 °		
		17,91	1383 °	18,41	1304 °	18,91	1245 °	19,41	1186 °		
		17,92	1381 °	18,42	1303 °	18,92	1244 °	19,42	1185 °		
		17,93	1379 °	18,43	1302 °	18,93	1243 °	19,43	1184 °		
		17,94	1377 °	18,44	1301 °	18,94	1242 °	19,44	1183 °		
		17,95	1375 °	18,45	1299 °	18,95	1240 °	19,45	1181 °		
		17,96	1373 °	18,46	1298 °	18,96	1239 °	19,46	1180 °		
		17,97	1371 °	18,47	1297 °	18,97	1238 °	19,47	1179 °		
		17,98	1370 °	18,48	1295 °	18,98	1237 °	19,48	1178 °		
		17,99	1368 °	18,49	1294 °	18,99	1236 °	19,49	1176 °		
		18,00	1366 °	18,50	1293 °	19,00	1235 °	19,50	1175 °		
		18,01	1364 °	18,51	1292 °	19,01	1234 °	19,51	1174 °		
		18,02	1363 °	18,52	1290 °	19,02	1233 °	19,52	1173 °		
		18,03	1361 °	18,53	1289 °	19,03	1231 °	19,53	1171 °		
		18,04	1359 °	18,54	1288 °	19,04	1230 °	19,54	1170 °		
		18,05	1357 °	18,55	1287 °	19,05	1229 °	19,55	1169 °		
		18,06	1356 °	18,56	1286 °	19,06	1228 °	19,56	1167 °		
		18,07	1354 °	18,57	1284 °	19,07	1227 °	19,57	1166 °		
		18,08	1352 °	18,58	1283 °	19,08	1226 °	19,58	1165 °		
		18,09	1351 °	18,59	1282 °	19,09	1225 °	19,59	1163 °		
		18,10	1349 °	18,60	1281 °	19,10	1223 °	19,60	1162 °		
		18,11	1348 °	18,61	1280 °	19,11	1222 °	19,61	1161 °		
		18,12	1346 °	18,62	1278 °	19,12	1221 °	19,62	1159 °		
		18,13	1344 °	18,63	1277 °	19,13	1220 °	19,63	1158 °		
		18,14	1343 °	18,64	1276 °	19,14	1219 °	19,64	1157 °		
		18,15	1341 °	18,65	1275 °	19,15	1218 °	19,65	1155 °		
		18,16	1340 °	18,66	1274 °	19,16	1216 °	19,66	1154 °		
		18,17	1338 °	18,67	1272 °	19,17	1215 °	19,67	1153 °		
		18,18	1337 °	18,68	1271 °	19,18	1214 °	19,68	1151 °		
		18,19	1335 °	18,69	1270 °	19,19	1213 °	19,69	1150 °		
		18,20	1334 °	18,70	1269 °	19,20	1212 °	19,70	1149 °		
		18,21	1332 °	18,71	1268 °	19,21	1211 °	19,71	1147 °		
		18,22	1331 °	18,72	1267 °	19,22	1209 °	19,72	1146 °		
		18,23	1329 °	18,73	1266 °	19,23	1208 °	19,73	1145 °		

 Powder Batch # : 278
 Date : 29/02/2016

 Batch approved
 Quality Inspection : 

 For inquiries :
 Customer Service Desk
 Phone : +49 69 27116 432
 Fax : +49 69 27116 243
