


**TEMPERATURE-TABLE for PTCR**

Higher quality products and lower costs through improved, reliable firing control

Type PTCR - STH		Ring Colour	: Green
Ferro no.	: 1400606	Dimensions	: ± 20 x 10 x 7,0 mm
Temperature Range °C	: 1130 - 1400°C		

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
				18,26	1319 °	18,76	1260 °	19,26	1206 °	19,76	1143 °
				18,27	1318 °	18,77	1259 °	19,27	1205 °	19,77	1142 °
				18,28	1317 °	18,78	1258 °	19,28	1204 °	19,78	1141 °
				18,29	1315 °	18,79	1257 °	19,29	1203 °	19,79	1139 °
		17,80	1402 °	18,30	1314 °	18,80	1256 °	19,30	1201 °	19,80	1138 °
		17,81	1400 °	18,31	1312 °	18,81	1255 °	19,31	1200 °	19,81	1136 °
		17,82	1397 °	18,32	1311 °	18,82	1254 °	19,32	1199 °	19,82	1135 °
		17,83	1395 °	18,33	1310 °	18,83	1253 °	19,33	1198 °	19,83	1134 °
		17,84	1393 °	18,34	1309 °	18,84	1252 °	19,34	1197 °	19,84	1132 °
		17,85	1391 °	18,35	1307 °	18,85	1251 °	19,35	1195 °	19,85	1131 °
		17,86	1389 °	18,36	1306 °	18,86	1250 °	19,36	1194 °	19,86	1130 °
		17,87	1386 °	18,37	1305 °	18,87	1249 °	19,37	1193 °		
		17,88	1384 °	18,38	1303 °	18,88	1248 °	19,38	1192 °		
		17,89	1382 °	18,39	1302 °	18,89	1247 °	19,39	1191 °		
		17,90	1380 °	18,40	1301 °	18,90	1246 °	19,40	1189 °		
		17,91	1378 °	18,41	1300 °	18,91	1244 °	19,41	1188 °		
		17,92	1376 °	18,42	1298 °	18,92	1243 °	19,42	1187 °		
		17,93	1374 °	18,43	1297 °	18,93	1242 °	19,43	1186 °		
		17,94	1372 °	18,44	1296 °	18,94	1241 °	19,44	1185 °		
		17,95	1370 °	18,45	1295 °	18,95	1240 °	19,45	1183 °		
		17,96	1368 °	18,46	1294 °	18,96	1239 °	19,46	1182 °		
		17,97	1366 °	18,47	1292 °	18,97	1238 °	19,47	1181 °		
		17,98	1364 °	18,48	1291 °	18,98	1237 °	19,48	1180 °		
		17,99	1362 °	18,49	1290 °	18,99	1236 °	19,49	1178 °		
		18,00	1361 °	18,50	1289 °	19,00	1235 °	19,50	1177 °		
		18,01	1359 °	18,51	1288 °	19,01	1234 °	19,51	1176 °		
		18,02	1357 °	18,52	1287 °	19,02	1233 °	19,52	1175 °		
		18,03	1355 °	18,53	1286 °	19,03	1232 °	19,53	1173 °		
		18,04	1353 °	18,54	1284 °	19,04	1231 °	19,54	1172 °		
		18,05	1352 °	18,55	1283 °	19,05	1229 °	19,55	1171 °		
		18,06	1350 °	18,56	1282 °	19,06	1228 °	19,56	1170 °		
		18,07	1348 °	18,57	1281 °	19,07	1227 °	19,57	1168 °		
		18,08	1347 °	18,58	1280 °	19,08	1226 °	19,58	1167 °		
		18,09	1345 °	18,59	1279 °	19,09	1225 °	19,59	1166 °		
		18,10	1343 °	18,60	1278 °	19,10	1224 °	19,60	1164 °		
		18,11	1342 °	18,61	1277 °	19,11	1223 °	19,61	1163 °		
		18,12	1340 °	18,62	1275 °	19,12	1222 °	19,62	1162 °		
		18,13	1339 °	18,63	1274 °	19,13	1221 °	19,63	1160 °		
		18,14	1337 °	18,64	1273 °	19,14	1220 °	19,64	1159 °		
		18,15	1335 °	18,65	1272 °	19,15	1218 °	19,65	1158 °		
		18,16	1334 °	18,66	1271 °	19,16	1217 °	19,66	1157 °		
		18,17	1332 °	18,67	1270 °	19,17	1216 °	19,67	1155 °		
		18,18	1331 °	18,68	1269 °	19,18	1215 °	19,68	1154 °		
		18,19	1329 °	18,69	1268 °	19,19	1214 °	19,69	1153 °		
		18,20	1328 °	18,70	1267 °	19,20	1213 °	19,70	1151 °		
		18,21	1326 °	18,71	1266 °	19,21	1212 °	19,71	1150 °		
		18,22	1325 °	18,72	1265 °	19,22	1211 °	19,72	1149 °		
		18,23	1323 °	18,73	1264 °	19,23	1209 °	19,73	1147 °		
		18,24	1322 °	18,74	1262 °	19,24	1208 °	19,74	1146 °		
		18,25	1321 °	18,75	1261 °	19,25	1207 °	19,75	1145 °		

Powder Batch #	: 286	Batch approved	
Date	: 20/02/2017	Quality Inspection	

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243

