

TEMPERATURE-TABLE for PTCR
Higher quality products and lower costs through improved, reliable firing control

Type PTCR - STH		Ring Colour	: Green
Ferro no.	: 1400606	Dimensions	: ± 20 x 10 x 7,0 mm
Temperature Range °C	: 1130 - 1400°C		

Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature	Ring dia-meter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
		19,85	1129	19,35	1202	18,85	1260	18,35	1328	17,85	1394
		19,84	1131	19,34	1203	18,84	1262	18,34	1329	17,84	1395
		19,83	1132	19,33	1204	18,83	1263	18,33	1331	17,83	1396
		19,82	1134	19,32	1206	18,82	1264	18,32	1333	17,82	1397
		19,81	1136	19,31	1207	18,81	1265	18,31	1334	17,81	1399
		19,80	1137	19,30	1208	18,80	1266	18,30	1336	17,80	1400
		19,79	1139	19,29	1209	18,79	1267	18,29	1337		
		19,78	1140	19,28	1211	18,78	1269	18,28	1339		
		19,77	1142	19,27	1212	18,77	1270	18,27	1340		
		19,76	1144	19,26	1213	18,76	1271	18,26	1342		
		19,75	1145	19,25	1214	18,75	1272	18,25	1343		
		19,74	1147	19,24	1216	18,74	1273	18,24	1344		
		19,73	1148	19,23	1217	18,73	1274	18,23	1346		
		19,72	1150	19,22	1218	18,72	1276	18,22	1347		
		19,71	1151	19,21	1219	18,71	1277	18,21	1349		
		19,70	1153	19,20	1221	18,70	1278	18,20	1350		
		19,69	1154	19,19	1222	18,69	1279	18,19	1351		
		19,68	1156	19,18	1223	18,68	1281	18,18	1352		
		19,67	1157	19,17	1224	18,67	1282	18,17	1354		
		19,66	1159	19,16	1225	18,66	1283	18,16	1355		
		19,65	1160	19,15	1226	18,65	1284	18,15	1356		
		19,64	1162	19,14	1228	18,64	1286	18,14	1357		
		19,63	1163	19,13	1229	18,63	1287	18,13	1358		
		19,62	1165	19,12	1230	18,62	1288	18,12	1359		
		19,61	1166	19,11	1231	18,61	1290	18,11	1361		
		19,60	1167	19,10	1232	18,60	1291	18,10	1362		
		19,59	1169	19,09	1233	18,59	1292	18,09	1363		
		19,58	1170	19,08	1235	18,58	1294	18,08	1364		
		19,57	1172	19,07	1236	18,57	1295	18,07	1366		
		19,56	1173	19,06	1237	18,56	1297	18,06	1367		
		19,55	1175	19,05	1238	18,55	1298	18,05	1368		
		19,54	1176	19,04	1239	18,54	1299	18,04	1369		
		19,53	1177	19,03	1240	18,53	1301	18,03	1371		
		19,52	1179	19,02	1241	18,52	1302	18,02	1372		
		19,51	1180	19,01	1243	18,51	1304	18,01	1373		
		19,50	1182	19,00	1244	18,50	1305	18,00	1375		
		19,49	1183	18,99	1245	18,49	1307	17,99	1376		
		19,48	1184	18,98	1246	18,48	1308	17,98	1377		
		19,47	1186	18,97	1247	18,47	1310	17,97	1378		
		19,46	1187	18,96	1248	18,46	1311	17,96	1380		
		19,45	1188	18,95	1249	18,45	1313	17,95	1381		
		19,44	1190	18,94	1250	18,44	1314	17,94	1382		
		19,43	1191	18,93	1251	18,43	1316	17,93	1383		
		19,42	1192	18,92	1253	18,42	1317	17,92	1385		
		19,41	1194	18,91	1254	18,41	1319	17,91	1386		
		19,40	1195	18,90	1255	18,40	1320	17,90	1387		
		19,39	1196	18,89	1256	18,39	1322	17,89	1389		
		19,38	1198	18,88	1257	18,38	1323	17,88	1390		
		19,37	1199	18,87	1258	18,37	1325	17,87	1391		
		19,36	1200	18,86	1259	18,36	1326	17,86	1392		

Powder Batch #	: 331	Batch approved	
Date :	07/10/2022	Quality Inspection :	

For inquiries :
 Customer Service Desk
 Phone : +49 69 27116 432
 Fax : +49 69 27116 243

